

**SYNTHETIC BUTYL RUBBER
BK-1675M**

BK-1675M is a product of isobutylene and isoprene copolymerization in methyl chloride medium. This type of rubber is used for production of medical articles.

CAS Number: 9010-85-9

Design specification: TU 2294-108-05766801-2001

PROPERTY	VALUE	TEST METHOD
Mooney Viscosity, ML 1+8 (125°C)	40-50	para. 4.3 of TU
Viscosity spread in one lot, max.	6	
Unsaturation, % mol.	1.4 - 1.8	para. 4.4 of TU
Loss of mass at drying, %, max.	0.40	para. 4.5 of TU
Stabilizer mass content, %	0.05 - 0.20	para. 4.6 of TU
Aqueous extract pH	6.5 - 7.5	para. 4.13 of TU
Tensile strength, MPa, min.	19	para. 4.7 of TU
Ultimate elongation, %, min.	600	para. 4.8 of TU
Modulus at 400% elongation, MPa, min.	7	para. 4.9 of TU
Ash mass content, %, max.	0.35	para. 4.10 of TU
Iron mass content, %, max.	0.020	para. 4.11 of TU
Antiagglomerate mass content, %, max.	1.2	para. 4.12 of TU

Supply form: 30±1 kg bales.

Packaging: Polyethylene film, wooden and metal pallet boxes.

Transportation: Product is transported by all means of transport.

Storage: Rubber in pallet boxes should be stacked maximum three tiers high. Storage in warehouses, away from direct sun-rays, atmospheric precipitation and contamination.

*The figures indicated on the table are standard values.